



Toll Free: 87 PERMATEx
(877-376-2839)

10 Columbus Blvd., Hartford,
Connecticut 06106

6875 Parkland Boulevard, Solon
Ohio 44139

Technical Data Sheet

Permatex® Super Weatherstrip Adhesive

AAM Revised 11/06

PRODUCT DESCRIPTION

Permatex® Super Weatherstrip Adhesive is a viscous liquid contact type cement for all types of weatherstripping. Super Weatherstrip Adhesive is an air-drying contact cement that allows quick bonding yet maintains enough versatility in tack to allow large areas to be spread and bonded at one time. The drying characteristics allow for repositioning parts after contact is made. The maximum strength of Super Weatherstrip Adhesive is attained after all the solvent has been released. Non-porous surfaces, if assembled while the adhesive is wet, will prevent the release of solvent, consequently, the adhesive will take longer to dry and develop maximum strength.

PRODUCT BENEFITS


- Water resistant
- Excellent chemical resistance
- Fast drying
- Withstands temperature extremes

TYPICAL APPLICATIONS

- Door and trunk moldings
- All types of automotive weatherstripping
- Body side moldings
- Decorative trim

DIRECTIONS FOR USE

1. Clean surfaces thoroughly. Use abrasives to remove any powdery mold release from the new weatherstripping.
2. Apply a thin, even film to both surfaces.
3. Allow to dry until the surfaces are tacky (about 3-4 minutes).
4. Bond the two surfaces together, and apply enough pressure to produce uniform contact.



Note: The early strength of Super Weatherstrip Adhesive is enough to hold most parts together. However, maximum strength is obtained after the

adhesive is completely dry. Aging of the bond and exposure to moderate heat increases strength.

For Cleanup

1. Use lacquer thinner or any hydrocarbon solvent while still wet.

PROPERTIES OF UNCURED MATERIAL

	Typical Value
Chemical Type	Neoprene Rubber
Appearance	Yellow viscous liquid
Odor	Solvent
Specific Gravity	0.88
Flash Point, TCC, °F	-10

TYPICAL CURING PERFORMANCE

Tack free time is 3-4 minutes. Substantial bond will form when the surfaces are mated. Maximum strength is obtained after the adhesive is completely dry, usually in 24 hours. Force drying with moderate heat will increase strength. Cure times will vary with temperature, humidity and gap.

TYPICAL ENVIRONMENTAL RESISTANCE

Temperature Resistance	Typical Values
Continuous, °C (°F)	-54 to 204 (-65 to 400)

Chemical / Solvent Resistance

The product retains effective properties in contact with automotive fluids, such as motor oil, transmission fluids, alcohol and antifreeze solutions.

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as an adhesive for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

ORDERING INFORMATION

Part Number	Container Size
81731 (80)	5 fl. oz. tube, boxed

STORAGE

Products shall be ideally stored in a cool, dry location in unopened containers at a temperature between 8° to 28°C (46° to 82°F) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused product, do not return any material to its original container.

NOTE

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. **Permatex, Inc. specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Permatex, Inc. products and disclaims any liability for consequential or incidental damages of any kind, including lost profits.** This product may be covered by one or more United States or foreign patents or patent applications.